ction Project (0704-0188), Washington, DC 20503. 1. AGENCY USE ONLY (Leave blank) Final 6/1/92 to 2. REPORT DATE to 5/30/96 11/1/96

4. TITLE AND SUBTITLE Biomimetic Fabrication of Functional Ceramic Composites

REPORT DOCUMENTATION

5. FUNDING NUMBERS AFSOR #

6. AUTHOR(S)

Sukenik, C., Heuer, A., and DeGuire, M.

49620-92-J-0282

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Department of Chemistry Case Western Reserve University 10900 Euclid Avenue

REPORT NUMBER

Cleveland, OH 44106-7078

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Dr. Frederick L. Hedberg AFSOR/NL 110 Duncan Avenue, Suite B115

Bolling AFB, DC 20332-0001

10. SPONSORING / MONITORING AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION / AVAILABILITY STATEMENT

12b. DISTRIBUTION CODE

Approved for public release

13. ABSTRACT (Maximum 200 words)

Thin films and multilayers of functional ceramics have a number of important applications including dielectrics, magnetic recording media, piezoelectric transducers, and integrated optical devices. Variously functionalized self-assembled monolayers, attached to single-crystal silicon substrates, were used to direct the deposition of thin films of the oxides of titanium, zinc, iron, and zirconium, at low temperatures and ambient pressures. The films were uniform, adherent, and pore-free and were, in many cases, comprised of micro-crystalline oxide particles. The monolayer functionality found to be most generally useful for these purposes included hydroxyl, carboxylate, and sulfonate functionality. In some cases the films contained desirable forms of the oxides that were different than those normally obtained: i.e., the anatase form of titania as opposed to rutile, and the tetragonal form of zirconia as opposed to monoclinic version. The patterning of the oxide films by patterning the underlying monolayer was also demonstrated. This project developed new technologies for the production of functional ceramics by creating templates for their deposition from solution and as such is a first step towards the generalized control of microstructural and crystallographic order by interface design in composite organic/inorganic materials.

14. SUBJECT TERMS			15. NUMBER OF PAGES
•			16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICATION OF ABSTRACT	20. LIMITATION OF ABSTRACT
. (	u	Li	46

Standard Form 298 (Rev Prescribed by ANSI Std 239-18 298-102

# FINAL TECHNICAL REPORT FOR AIR FORCE OFFICE OF SCIENTIFIC RESEARCH

Biomimetic Fabrication of Functional Ceramic Composites Project Period: 6/1/92 - 5/30/96 AFOSR #49620-92-J-0282

Departments of Chemistry and Materials Science Engineering
Case Western Reserve University
Cleveland, OH 44106

#### Personnel

Principal Investigator Sukenik, Chaim N. (Prof., Chemistry)
Faculty Co-Investigator Heuer, Arthur H. (Prof., Materials Science)

Faculty Co-Investigator DeGuire, Mark R. (Assoc. Prof.., Materials Science)

Grad. Stud. Co-Investigator
Shin, Hyun J. (Materials Science)

Grad. Stud. Co-Investigator Sitthisuntorn Supothina (Materials Science)

Post Doc. Co-Investigator Wang, Yoo Hoo (Materials Science)
Undergrad. Co-Investigator Pfefferkorn, Jeffrey (Chemistry)

#### **Abstract**

Thin films and multilayers of functional ceramics have a number of important applications including dielectrics, magnetic recording media, piezoelectric transducers, and integrated optical devices. Variously functionalized self-assembled monolayers, attached to single-crystal silicon substrates, were used to direct the deposition of thin films of the oxides of titanium, zinc, iron, and zirconium, at low temperatures and ambient pressures. The films were uniform, adherent, and pore-free and were, in many cases, comprised of micro-crystalline oxide particles. The monolayer functionality found to be most generally useful for these purposes included hydroxyl, carboxylate, and sulfonate functionality. In some cases the films contained desirable forms of the oxides that were different than those normally obtained: i.e., the anatase form of titania as opposed to rutile; and the tetragonal form of zirconia as opposed to monoclinic version. The patterning of the oxide films by patterning the underlying monolayer was also demonstrated. This project developed new technologies for the production of functional ceramics by creating templates for their deposition from solution and as such is a first step towards the generalized control of microstructural and crystallographic order by interface design in composite organic/inorganic materials.

#### Patents

Mark R. DeGuire, Arthur H. Heuer, and Chaim N. Sukenik; Synthesis of Metal Oxide Thin Films U.S. Patent No 5,352,48, issued 4 October 1994. Additional continuation in part issued in 1996.

### Student theses submitted to CWRU

Ph.D. theses of Rochael J. Collins (Chemistry, 1997) and Hyunjung Shin (Material Science, 1996) and M. Sc. theses of Hyunjung Shin (Material Science, 1994), Mou Maiti (Material Science, 1995) and Sitthisuntorn Supothina (Material Science, 1995).

## Published scientific papers in professional journals:

- 1) "Synthesis and Characterization of TiO<sub>2</sub> Thin Films on Organic Self-Assembled Monolayers: I. Film Formation from Aqueous Solutions", Shin, H.; Collins, R.J.; DeGuire, M.R.; A.H.; Sukenik, C.N. *Journal of Materials Research*, 10, 692-698 (1995).
- 2) "Synthesis and Characterization of TiO<sub>2</sub> Thin Films on Organic Self-Assembled Monolayers: II. Film Formation via an Organometallic Route", Shin, R.; Collins, R.J.; DeGuire, M.R.; Heuer, A.H.; Sukenik, C.N. *Journal of Materials Research*, 10, 699-703 (1995).
- 3) "Sulfonate-Functionalized, Siloxane-Anchored, Self-Assembled Monolayers", Collins, R.J.; Sukenik, C.N. *Langmuir*, 11, 2322-2324 (1995).
- 4) "Deposition of Oxide Thin Films on Silicon using Organic Self-Assembled Monolayers", DeGuire, M.R.; Shin, H.; Collins, R.; Agarwal, M.; Sukenik, C.N.; Heuer, A.H. Integrated Optics and Microstructures III, M. Tabib-Azar Ed., Proc. SPIE, 2689, 88-99 (1966).
- 5) "Low Temperature Deposition of Patterned TiO<sub>2</sub> Thin Films Using Photopatterned Self-Assembled Monolayers", Collins, R.J.; Shin, H.; DeGuire, M.R.; Sukenik, C.N.; Heuer, A.H. Applied Physics Letters, 69, 860-862 (1996).
- 6) "Photocontrolled Formation of Hydroxyl-Bearing Monolayers and Multilayers", Collins, R.J.; Bae, I.T.; Scherson, D.A.; Sukenik, C.N. *Langmuir*, 12, 0000 (November, 1996).
- 7) "Solid-State Diffusive Amorphization in TiO<sub>2</sub>/ZrO<sub>2</sub> Bilayers", Shin, H.J.; Agarwal, M.; DeGuire, M.R.; Heuer, A.H. J. Amer. Cer. Soc., 79, 1975-1978 (1996).